

PComP™: Nano-Composite Thermal Spray Alternative to Cd and Cr

SERDP/ESTCP Workshop Tempe, AZ

February 26-28, 2008

Greg Engleman
Powdermet Inc.
Euclid, OH 44117
(216) 404-0053
www.powdermetinc.com

maintaining the data needed, and c including suggestions for reducing	lection of information is estimated to completing and reviewing the collecti this burden, to Washington Headquuld be aware that notwithstanding an OMB control number.	ion of information. Send comments rarters Services, Directorate for Information	egarding this burden estimate of mation Operations and Reports	or any other aspect of the 1215 Jefferson Davis	nis collection of information, Highway, Suite 1204, Arlington	
1. REPORT DATE FEB 2008		2. REPORT TYPE		3. DATES COVE 00-00-2008	RED 3 to 00-00-2008	
4. TITLE AND SUBTITLE		5a. CONTRACT NUMBER				
PComPtm: Nano-C	Composite Thermal	Cd and Cr	5b. GRANT NUMBER			
					5c. PROGRAM ELEMENT NUMBER	
6. AUTHOR(S)					5d. PROJECT NUMBER	
					5e. TASK NUMBER	
					5f. WORK UNIT NUMBER	
7. PERFORMING ORGANIZATION NAME(S) AND ADDRESS(ES) Powdermet Inc,24112 Rockwell Dr,Euclid,OH,44117				8. PERFORMING ORGANIZATION REPORT NUMBER		
9. SPONSORING/MONITO	RING AGENCY NAME(S) A	10. SPONSOR/MONITOR'S ACRONYM(S)				
				11. SPONSOR/M NUMBER(S)	ONITOR'S REPORT	
12. DISTRIBUTION/AVAII Approved for publ	LABILITY STATEMENT ic release; distributi	on unlimited				
U	OTES And Repair Issues fo Sponsored by SERD	O	ilitary Aircraft V	Vorkshop, Fo	ebruary 26-28,	
14. ABSTRACT						
15. SUBJECT TERMS						
16. SECURITY CLASSIFIC	17. LIMITATION OF ABSTRACT	18. NUMBER OF PAGES	19a. NAME OF RESPONSIBLE PERSON			
a. REPORT unclassified	b. ABSTRACT unclassified	c. THIS PAGE unclassified	Same as Report (SAR)	18	ALSI ONSIBLE FEASON	

Report Documentation Page

Form Approved OMB No. 0704-0188

Acknowledgments

- EPA Phase I SBIR CONTRACT # EP-D-06-053
 - Metastructured Cermets for Hard Chrome Replacement
- Ohio Third Fronter Grant ORCGP-04-063
 - Commercialization of MicroComposite Powders
- NASA SBIR Grant NNC07QA06P
 - Erosion Resistant Compressor Blade Repair Technologies
- National Science Foundation 637502
- Boeing –Fatigue testing and data
- PTI –HVOF Coating Services



Outline

- Introduction to Powdermet
- Hierarchically Structured Materials
- PComPTM
- Work Plan
- Testing
- Conclusion



Powdermet

- Application Driven Powder Development Company
- Specializing in Powder Modification
 - Particle Size Engineering
 - Bottom up/Top Down
 - Compositing
 - Agglomeration
 - Particle Coating
- Develop Powders to Meet Specification




Microcomposite coating Materials Approach

- Combine hardness of lightweight ceramic with ductility and toughness of metal
 - Start with low cost, lightweight ceramic (Al2O3 or SiC, -Si3N4 for low friction). 3-4g/cc, 0.1-1 micron particle size
 - Blend and Spray-dry with corrosion resistant ductile metal alloy binder (Ni baseline)
 - Keep structure nanocrystalline, high hardness, corrosion resistance, and strength
 - Encapsulate with additional matrix for toughness/ductility
 - Micron-scale "lamella" in coating to allow for dislocation motion (ductility)
 - Thermal spray to form ductile wear and corrosion resistant coatings.
 - Laser fuse, cold-spray alternatives
 - Patent-pending materials technology



The Micro/Nanocomposite solution

- nanocomposite provides high wear resistance, low friction
- Ductile binder provides ductility and toughness
- Working on HVOF, laser cladding, cold spray, and spray and fuse powder designs



Microcomposite coating features

	Micro-Composite Coatings	Chrome Plate	WC-Co-Cr thermal spray
Coating density	4-5g/cc (low)	9g/cc (medium)	17g/cc (very high)
Total coating cost	Less than 1X	Baseline (1X)	2X
modulus	20-30MSI	0 (cracked)	65 MSI
Gun throughput	>3X	Days to coat	1X
Surface finishing costs	SiC or alumina wheel	Alumina wheel	Diamond wheel
Ductility	4%	<0% (cracked)	<1%
Wear Performance	10X chrome	1X chrome	3X chrome
Thickness limitations	>40 mils	3-5 mils	10-20 mils



PComPTM

- Drop-In Replacement for Thermal Spray Materials
- Reduced Density (3.5-6.5 g/cm³)
- Doesn't Require Special Tooling
 - ■No Diamond/CBN Grinding
- Low-
 - **■**Density, Friction, Stiffness



PComP ™ Materials


- **■WC-Co**
 - ■Applied by PTI
 - ■Tested by Boeing
- **■** Core Reinforcements
 - \blacksquare TiN, Si₃N₄, TiC, Al₂O₃
- Metal Binders
 - ■Ni, Ni-Cr, Ni-Cr-Mo



Powder design variables


Core: diameter, density, grain size, pore size, metal/ceramic

 $V^0/_0$




Coating: composition, thickness

Nanocomposite Powders Developed






DJ- Cut, HVOF powders






Composite Structure



Fatigue life for bare and coated samples at different test stress conditions



Axial tension-compression fatigue (R= -1.0), in room temperature air, at 2 Hz. Fatigue specimens were cylindrical bar 8 inches long, 0.75 inches in diameter, with an hourglass shape narrowing to a minimum of 0.3 inches. The fatigue debit as a result of coating is less than a factor of 2.



Fatigue Data Observations: Notes from Test Operator


Specimen Number	Cycles to Failure	Notes
7604-10 C	2,120	No spalling before failure
7604-12 C	2,129	Crack in coating at 750 cycles. Spalling at 1500 cycles.
7604-13 C	2,258	No spalling before failure
7604-14 C	1,949	No spalling before failure







Left side Right side





Closing

- Hierarchically Structured Coatings Offer Numerous Advantages
- PComPTM Improves on Meso-Structured Composite Materials
- PComPTM Can Meet Rigorous Landing Gear Requirements (AF/Navy/Civilian)
- Need Specifications for Materials Design



QUESTIONS? COMMENTS